

DLS-1 TECHNICAL DATA SHEET

FOR PRO-SEAL 6006 AND PRO-SEAL 6006EX

The proportion of catalyst to sealer is not very critical in obtaining a complete cure. The quantity of catalyst can be adjusted depending on climatic conditions. Use less catalyst in hot weather and more catalyst in cold weather. Each gallon of Pro-Seal is supplied with two (2) 1 ounce tubes of catalyst. Extra catalyst can be purchased separately by calling RAI Products Toll Free @ 1-888-PRO-SEAL.

Use the chart below to determine the amount of catalyst to use.
(N/R=Not Recommended)

Tubes Per Gallon	Ambient Temperature						
	30°-45°	45°-55°	55°-65°	65°-75°	75°-80°	80°-90°	90°+
1 Tube	N/R	N/R	N/R	N/R	N/R	N/R	12-18 Min.
2 Tubes	N/R	30-35 Min.	25-30 Min.	20-25 Min.	15-20 Min.	10-15 Min.	Under 10 Min.
3 Tubes	20-25 Min.	15-20 Min.	10-15 Min.	7-10 Min.	N/R	N/R	N/R

To thicken Pro-Seal for use on steep inclines dry sand may be added during the mixing process. Dry sand may be spread on top of Pro-Seal to make it instantly tack free. Sand is especially helpful for lead-ins across open lanes of traffic.

The coverage chart below is for 1 gallon of Pro-Seal.

Depth	Slot Width				
	3/16"	1/4"	5/16"	3/8"	1/2"
1"	100'	80'	66'	53'	40'
1 1/2"	75'	53'	45'	36'	27'
2"	50'	40'	33'	26'	20'
3"	36'	27'	23'	18'	14'